

CDS - 8110

2 mil EVA with Taffeta Finish on Low Tack Paper Carrier

General Information

- EVA/LDPE copolymer resin film with 8.7% vinyl acetate with thermal stabilizer
- Finish: Taffeta/Matte
- Low-tack paper carrier with no adhesive transfer laminated to matte finish side

Physical Properties

Thickness (Taffeta Finish)	3.7 +/- 0.3	mil	PTM - QA- 005
Thickness (Matte Finish)	2.0 +/- 0.3	mil	PTM - QA- 005
Density	0.930	g/cm ³	ASTM - D1505
Gloss (60°)(Matte/Taffeta)	20.7/14	GU	ASTM - D2457
Transmittance (Film)	46	%	ASTM - E792

Mechanical Properties

Tensile Elongation at Break (MD/TD)	190/455	%	ASTM - D882
Tensile Strength at Break (MD/TD)	3820/2425	psi	ASTM - D882
Peel from Film	11	g/in	ASTM - D3330 Method A

Thermal Properties

Vicat Softening Temperature	77	°C	ASTM - D1525
Melt Mass - Flow Rate (MFR) (190°C/2.16kg)	2.0	g/10 min	ASTM - D1238
Melting Temperature	100	°C	ASTM - E1356
Peak Crystallization Temperature	85	°C	ASTM - D3418

Shelf Life

1 year after date of manufacture

Technical Information Notes

Taffeta finish increases the original film thickness by almost 2 mil thickness. Original film thickness with matte finish is 2.0 +/- 0.3 mil.

Original Issue Date- 4/13/2020

Approval Date- 5/28/2020 Revision- A

Listed Values:

The above values are typical property values not to be construed as specification limits.

CLAIMS, WARRANTIES, AND LIMITATIONS OF LIABILITY:

- (a) Buyer waives at claims relating to the goods unless received in writing by Seller within thirty (30) days of receipt of the goods. No goods shall be returned by Buyer for any reason without Seller's written approval
- (b) ALL WARRANTIES RELATING TO THE DESCRIBED GOODS ARE EXPRESSED IN THIS PARAGRAPH (5b). SELLER MAKES NO WARRANTY, EXPRESS, IMPLIED OR STATUTORY WITH RESPECT TO THE GOODS AND SELLS THEM AS IS EXCEPT THAT SELLER WILL BE RESPONSIBLE, TO BUYER ONLY, FOR FAULTY WORKMANSHIP AND USE OF IMPERFECT MATERIALS
- (c) SELLER SHALL NOT BE LIABLE UNDER ANY CIRCUMSTANCES TO BUYER OR ANY OTHER PERSON WHERE THE GOODS ARE NOT WAREHOUSED, HANDLED OR USED IN ACCORDANCE WITH PROPER AND CUSTOMARY PRACTICES OF THE TRADE.
- (d) BUYER'S EXCLUSIVE REMEDY AND SELLER'S SOLE LIABILITY ON ANY CLAIM, WHETHER TORT, CONTRACT, OR WARRANTY, SHALL BE LIMITED TO REPLACEMENT OF THE DEFECTIVE GOODS OR, AT SELLER'S OPTION, TO REIMBURSEMENT OF BUYER'S ACTUAL COST OF THE GOODS NOT SO REPLACED AND IN NO EVENT SHALL SELLER BE LIABLE FOR INDEMNIFICATION OF BUYER ON ACCOUNT OF ANY CLAIM ASSERTED AGAINST BUYER FOR ANY OTHER OR FURTHER DAMAGES OF ANY KIND WHATSOEVER, WHETHER DIRECT OR INDIRECT.

(e) Buyer may not bring any action arising hereunder unless such action is commenced within one (1) year after the cause of action has accrued.

LIMITATION OF LIABILITY:

Except for the limited remedy stated above, and except to the extent prohibited by law, Plitek will not be liable for any loss or damage arising from or related to the Plitek product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Trademarks:

Plitek is a trademark of Plitek, L.L.C